

## Технические характеристики геосетки ПолиЭф-Грунт

Марка геосетки	Пропитка	Подложка	Поверхностная плотность, не менее (г/м <sup>2</sup> )	Разрывная нагрузка, кН/м, - продольная	Разрывная нагрузка, кН/м, - поперечная	Относительное удлинение			
20/20	ПВХ	нет	230	20	20	≤ 12,5 %			
30/30			280	30	30				
35/35			310	35	35				
40/20			300	40	20				
40/40			330		40				
50/20			310	50	20				
50/50			380		50				
60/20			410	60	20				
60/60			450		60				
65/65			500	65	65				
80/30			540	80	30				
80/80			600		80				
100/30			590	100	30				
100/100			640		100				
110/30			650	110	30				
110/110			600		110				
150/30			540	150	30				
150/150			1000		150				
200/50			870	200	50				
200/200			1400		200				
250/50			1000	250	50				
250/250			1750		250				
250/250					1750			250	
300/50					1200		300	50	
300/300					2100			300	
400/50			1500	400	50				
400/400			2800		400				
500/50			1900	500	50				
500/500			3500		500				
600/50			2300	600	50				
600/400			3500		400				
700/50			2600	700	50				
800/50			2950	800					
900/50			3300	900					
1000/100			3850	1000	100				